



Matte PLA Filament

1.75 mm · 1 kg spool

OzFDM PLA Matte 3D printing filament is specially produced for a matte surface finish. This filament offers exceptional bed and layer adhesion, no warping/cracking, and remarkable dimensional stability; all within strict QA standards. Users will enjoy an easy, consistent, and reliable printing experience with 100% biodegradable, FDA-approved safety and quality assured PLA.

✓ Smooth matte surface finish

✓ Excellent bed & layer adhesion

✓ No warping or cracking

✓ Biodegradable PLA

RECOMMENDED PRINT SETTINGS

Nozzle temperature	190 – 220 °C
Bed temperature	25 – 60 °C
Print speed	60 – 90 mm/s
Support material	PVA, PETG (interface)
Drying	40 – 45 °C for 4 – 6 h

FILAMENT SPECIFICATIONS

Diameter	1.75 mm
Dimensional tolerance	± 0.03 mm
Net weight	1 kg
Density	1.25 – 1.26 g/cm ³

SPOOL & PACKAGING

Empty spool weight	150 g
Full spool weight	1.15 kg
Spool outer diameter	200 mm
Spool hub diameter	52 mm
Spool width	65 mm
Shipping weight	1.3 kg
Box dimensions	210 × 210 × 75 mm

MECHANICAL PROPERTIES

Tensile Strength ISO 527	45 – 49 MPa
Elongation at Break ISO 527	13.5 – 15.5 %
Flexural Modulus ISO 527	1000 – 1100 MPa
Flexural Strength ISO 178	69 – 75 MPa
Impact Strength ISO 180	4.5 – 5 kJ/m ²


THERMAL & PHYSICAL PROPERTIES

Heat deflection (0.455 MPa) ISO 75	53 °C
Continuous Use Temperature IEC 60216	50 °C
Melt flow rate (250 °C/2.16 kg) ISO 1133	4 – 8 g/10 min
Moisture absorption (23 °C/24 h) ISO 62	< 0.3 %

STORAGE & HANDLING

Airtight bag or container with desiccant in a cool, dark, dry place. For long-term storage, dry the filament before vacuum-sealing it with desiccant.

PROPERTY PROFILE



AVAILABLE COLOURS (22)

