



PETG Tool Colours Filament

1.75 mm · 1 kg spool

OzFDM PETG+ filament is made from high quality specially modified PETG material. This offers low warping, non-cracking and low print and bed temperatures, making it easier to print than standard PETG while still maintaining its high strength and heat resistance.

✓ Tool-brand colour matches

✓ Easier to print than standard PETG

✓ Strong & heat resistant

RECOMMENDED PRINT SETTINGS

Nozzle temperature	220 – 240 °C
Bed temperature	50 – 80 °C
Print speed	40 – 60 mm/s
Support material	PVA, PLA (interface)
Drying	70 °C for ≥ 5 h

FILAMENT SPECIFICATIONS

Diameter	1.75 mm
Dimensional tolerance	± 0.03 mm
Net weight	1 kg
Density	1.27 – 1.28 g/cm ³

SPOOL & PACKAGING

Empty spool weight	150 g
Full spool weight	1.15 kg
Spool outer diameter	200 mm
Spool hub diameter	52 mm
Spool width	65 mm
Shipping weight	1.3 kg
Box dimensions	210 × 210 × 75 mm

MECHANICAL PROPERTIES

Tensile Strength ISO 527	41 – 45 MPa
Elongation at Break ISO 527	10 – 12 %
Flexural Modulus ISO 527	1400 – 1500 MPa
Flexural Strength ISO 178	64 – 66 MPa
Impact Strength ISO 180	5 – 6 kJ/m ²


THERMAL & PHYSICAL PROPERTIES

Heat deflection (0.455 MPa) ISO 75	74 °C
Continuous Use Temperature IEC 60216	70 °C
Melt flow rate (250 °C/2.16 kg) ISO 1133	4 – 6 g/10 min
Moisture absorption (23 °C/24 h) ISO 62	< 0.2 %

STORAGE & HANDLING

Airtight bag or container with desiccant in a cool, dark, dry place. For long-term storage, dry the filament before vacuum-sealing it with desiccant.

PROPERTY PROFILE



AVAILABLE COLOURS (4)



Mil-Walkie



Mah-Keeta



Dee-Walt



Rye-obi